



## ARC TABLE TOP ULTRA CLEAR CASTING EPOXY RESIN SET

### PRODUCT INFORMATION:

RESIN	HARDENER	MIX RATIO
<b>ARC TABLE TOP</b>	<b>CLEAR HARDENER</b>	<b>100/33 (WEIGHT-VOLUME)</b>

Two component –any solvent ultra transparent casting type epoxy resin system. Suitable for all decorative application like furniture application ( clear epoxy table ), wood coating, epoxy resin cube ,3d floor covering, electrical led system coating, gift of jewelery etc.

### PROPERTIES:

- Ultra transparent view
- Not any yellowing
- Crystal shine
- Extra UV
- Not any air bubbles
- Wonderful strength
- Perfect surface flatness

### TECHNICAL DETAILS;

High modulus un-filled epoxy system. The curing agent should be selected according to the application. The curing at room temperature plus the post-curing at moderate temperatures (50-60°C) allows high performance. Further stabilization at higher temperatures improves the thermal resistance of the components.

**SOLID VOLUME : %100- APPLICATION DEGREE: 15-35 °C-**

## SYSTEM SPECIFICATIONS

### Resin

Viscosity	25°C	IO-10-50 (EN13702-2)	mPas	1.200	1.800
-----------	------	----------------------	------	-------	-------

### Hardener

Viscosity	25°C	IO-10-50 (EN13702-2)	mPas	10	15
Gelation time	25°C	IO-10-52a (UNI 8701)	Min.	240	360

### Resin

Colour				Ultra Clear	
Density	25°C	IO-10-51 (ASTM D 1475)	g/ml	1,06-1,10	

### Hardener

Colour				Ultra Clear	
Viscosity	25°C	IO-10-50 (EN13702-2)	mPas	10	15
Density	25°C	IO-10-51 (ASTM D 1475)	g/ml	0,92-0,96	

## TYPICAL SYSTEM CHARACTERISTICS

Mix Ratio		for 100 g resin	g	100:25	
Pot life	25°C	(50mm;200ml)	IO-10-53 (*)	Min.	120-150
Exothermic peak	25°C	(50mm;200ml)	IO-10-53 (*)	°C	65
Gelation time	25°C	(1mm)	IO-10-88	hour	4 6
Demoulding <Time	25°C	(15ml;6mm)		hour	12-18